

QUALITY CERTIFICATE

Product	Portland Cement Type 2 ( M 400)
Standard	ISIRI 389,EN197-1,GOST 10178
Ship	
Date	

Producer	Peyvand Golestan Cement Co First Floor, Nr. 1, Secand Alley, Pakistan St., Beheshti St., Tehran Tel : 021 88175135 , 88174029 Fax : 02188174081 <a href="http://www.Pgcement.ir">www.Pgcement.ir</a>
Email:	<a href="mailto:pgcement@pgcement.ir">pgcement@pgcement.ir</a>

Physical Properties	Factory test result	Standard (ISIRI-389)	GOST 10178	Unit
Setting Time (Vicat ,Initial)	175	Min 45	Min 45	Minute
Setting Time (Vicat ,Final)	3.4	Max 6:00	Max 10:00	hr
Expansion (Autoclave)	0.1	Max 0.8	Max 0.8	%
Specific Surface Area (Blaine)	3150	Min 2800	Min 2800	cm2/gr
Residue on 90m Sieve	1			%
Compressive Strength (1 day)				kg/cm2
Compressive Strength (2 days)				kg/cm2
Compressive Strength (3 days)	250	Min 100		kg/cm2
Compressive Strength (7 days)	375	Min 175		kg/cm2
Compressive Strength (28 days)	490	Min 315	Min400	kg/cm2

Chemical Analysis	Factory test result	Standard (ISIRI - 389)	GOST 10178	Unit
SiO2	20.75	Min 20.00		%
Al2O3	5.21	Max 6.00		%
Fe2O3	3.64	Max 6.00		%
CaO	63.05	.....		%
MgO	1.8	Max 5.00	Max 5.00	%
SO3	2.6	Max 3.00	Max 3.50	%
Insoluble Residue	0.34	Max 0.75		%
Loss On Ignation	1.98	Max 3.00		%
Free CaO	1.2			%
K2O	0.50			%
Na2O	0.3			%

Modulus	Factory test result	Standard ( ISIRI - 389)	GOST 10178	Unit
Lime Saturation Factor (LSF)	91.92			%
Silica Modulus (SM)	2.34			
Alomina Modulus (AM)	1.43			

Mineralogical Composition	Factory test result	Standard ( ISIRI - 389)	GOST 10178	Unit
C3S	51.43			%
C2S	20.98			%
C3A	7.65	Max 8.00		%
C4AF	11.07			%

Factory Management

Lab &QC Manager



